

# An Optimally Solving Dentistry Internal Purity in Heat Polymerized Acrylic Resin With Different Polymerization Methods

*by* Sajaratud Dur Sajaratud Dur

---

**Submission date:** 02-Feb-2021 03:48PM (UTC+0700)

**Submission ID:** 1499793582

**File name:** optimally\_solving\_dentistry\_internal\_purity\_-\_Sajaratud\_Dur.pdf (519.63K)

**Word count:** 4601

**Character count:** 23637

# AN OPTIMALLY SOLVING DENTISTRY INTERNAL PURITY IN HEAT POLYMERIZED ACRYLIC RESIN WITH DIFFERENT POLYMERIZATION METHODS

Sajaratud Dur<sup>1</sup>, Ismail Husein<sup>2</sup>, Muqdad Irhaeem Kadhim<sup>3</sup>, Hasan Shamran Mohammed<sup>4</sup>, \*Marischa Elveny<sup>5</sup>, Rahmad Syah<sup>6</sup>, Lelya Hilda<sup>7</sup>

<sup>1</sup>Department of Mathematics, Universitas Islam Negeri Sumatera Utara, Medan

<sup>2</sup>Department of Mathematics, Universitas Islam Negeri Sumatera Utara, Medan

<sup>3</sup>College of sciences, University of Al-Qadisiyah, Iraq

<sup>4</sup>College of sciences, University of Al-Qadisiyah, Iraq

<sup>5</sup>Faculty of Computer Science and Technology Information, Universitas Sumatera Utara, Medan, Indonesia

<sup>6</sup>Faculty of Computer Science and Technology Information, Universitas Sumatera Utara, Medan, Indonesia

<sup>7</sup>IAIN Padangsidempuan

## ABSTRACT

A Polymerization Method for dentistry is a collaboration poured into the knowledge base by combining different chemical reactions and polymerization methods. In this study, The results of this study indicated that there was a difference in the amount of internal porosity in the hot polymerized acrylic resin with different methods in sample group A (temperature 25 ° C for 0' → 74 ° C for 90' → 100 ° C for 60'), namely 11,520 in the sample group. B (temperature 25 ° C for 0' → 70 ° C for 90' → 100 ° C for 30') which is 7,860 and the sample group C (temperature 25 ° C for 0' → 74 ° C for 60' → 100 ° C for 30') 14,150, slightly compared to sample A (temperature 25 ° C for 0' → 74 ° C for 90' → 100 ° C for 60') and sample C (temperature 25 ° C for 0' → 74 ° C for 60' → 100 ° C for 30'). The temperature of the polymerization process does not exceed the boiling point of the monomer, the amount of porosity contained in the acrylic resin will be low, the monomer boiling point is 100.8 ° C.

**Keywords:** Optimally Solving Dentistry, Different Polymerization Method, and Polymerization Acrylic Resin.

## Correspondance:

Marischa Elveny

Faculty of Computer Science and Technology Information, Universitas Sumatera Utara,

Medan, Indonesia

Email id : marischaelveny@usu.ac.id

## INTRODUCTION

Acrylic resin has been used in dentistry as a base for dentures. Acrylic resin is a thermoplastic material that is formed by combining methacrylate molecules. In general, acrylic resins can be divided into three types, namely self-polymerized acrylic resins, light-polymerized acrylic resins, and hot-polymerized acrylic resins. Hot polymerized acrylic resin is still in great demand as a base material for dentures because it has a fairly good aesthetic quality, low water absorption and is easy to process so that many processing methods have been developed for the purpose of minimizing the occurrence of shrinkage. Acrylic resin often experiences porosity and strength, and the hardness becomes fewer causing cracks or fractures of the denture base after several uses. Porosity occurs because the mixing process between powder and liquid is not good so that air is trapped and evaporation of monomers during the polymerization process. Acrylic resin polymerization methods have also developed due to developments in science, technology and dental materials. The polymerization methods commonly used are heating using infrared, water bath and microwave methods. Research conducted by (Luay N Abood, 2007) which used different polymerization methods and different thicknesses of acrylic resin, namely using conventional and microwave methods, the results of this study said that there were differences in the porosity of acrylic resin, conventional methods had less porosity. Previous research was also carried out by (Moosa R, 2012) who conducted research on the effect of the acrylic resin polymerization method on porosity at different temperatures and times. His research used different temperatures, 70 ° for 45 minutes, 70 ° for 7 hours, 70 ° for 9 hours, and 60 minutes. The results of this study indicate that

there is a difference in the amount of porosity using a low temperature and a long time the porosity value in acrylic resin is less, namely at 70° for 9 hours the porosity value is 02.0%. (Mohammed T. Al-Khafagy et al, 2013) examined using conventional polymerization methods with different times, with the results that there were significant differences between samples using a polymerization time of 100°C for 30 minutes compared to those using a polymerization time of 74°C for 2 hours. The polymerization method with a long polymerization time had less porosity than a fast polymerization time. (Sunint Singh, et al, 2013) examined the evaluation of the surface porosity of hot polymerized acrylic resin using a water bath and microwave. The result of this research is using water bath there is a little porosity. Microwave-based acrylic resin has a significant increase in porosity compared to water bath. Research conducted by (Sahela Nisar et al, 2015) examined the effect of polymerization variations and different powder and liquid ratios on the strength and porosity of acrylic resin, in this study using different specimens, namely 25°C for 0 minutes then increased 70°C for 90 minutes then raised again. 100°C for 60 minutes, 25°C for 0 minutes then set the temperature to 70°C for 60 minutes, then raise the temperature again to 100°C for 30 minutes, 70°C for 0 minutes then raise the temperature again to 100°C for 30 minutes, 100°C for 0 minutes then raise the temperature again to 100°C for 30 minutes. The results of this study showed a large porosity of the specimens which were directly placed at boiling water temperature of 100°C. This research was conducted to see the amount of internal porosity in hot polymerized acrylic resin when it was carried out using different polymerization methods.

## An Optimally Solving Dentistry Internal Purity In Heat Polymerized Acrylic Resin With Different Polymerization Methods

In this study, there are 3 types of acrylic resins used in dentistry, namely heat-cured acrylic resins, self-cured self-polymerizing acrylic resins, and light-cured resins. Acrylic resins that are widely used in the manufacture of dentures are


### RESEARCH AND METHODOLOGY

heat cured acrylic resins.

1. At this stage the polymer and monomer gradually mix to form a precipitate. The monomers will
2. polymer granules remain unchanged and the

gradually seep into the polymer to form a fluid that is not united. During this stage, there is little or no interaction at the molecular level. The

- b) Polymerization: The cuvette was then heated



**Figure 1.** Polymerization of acrylic resin through 5 steps during mixing

consistency of the mixture is still coarse and granular.

3. In the second stage the monomer will begin to seep or enter the polymer surface. The polymer chain will be dispersed in the monomer fluid. This polymer chain will release the bonds thus increasing the thickness of the mixture. At this stage the mixture will be fibrous in the form of threads and will be sticky when touched or pulled.
  4. In the third stage the mixture will be smoother and more homogeneous. The mixture will no longer stick to the touch with your hands or a spatula. At this stage, the mixture is ready to be formed and put into the mould.
  5. In the fourth stage there is no more monomer left, because the monomer has fully absorbed the polymer and part of the monomer evaporates. The mass at this stage is already plastic and can no longer be formed and inserted into the mould.
  6. In the fifth stage, it appears that the dough will become hard and stiff, this is due to the evaporation of free monomers. Clinically the mixture looks very dry.
- a) fulfilment: After the dough reaches the dough stage, the dough is put into the mould on the cuvette. After filling the dough, the first press is carried out with a pressure of 1000 psi to reach the mould is filled densely and the excess resin is removed then the final press is carried out with a pressure of 2200 psi then the cuvette is locked. Then the cuvette was left at room temperature for 30-60 minutes.

using a water bath at 70 °C for 90 minutes and continued with 100 °C for 30 minutes.

- c) refrigeration: After heating, the cuvette was left in the water bath for 30 minutes for cooling. After that the cuvette was placed under running water for 15 minutes and allowed to cool to room temperature.

### MATERIAL AND METHOD


#### 3.1. Polymerization Method

There are several polymerization methods of acrylic resin for prosthetic bases of various sizes, shapes and thicknesses. One of the polymerization methods according to Inservice is to use a water bath with a constant temperature of 74 °C for 8 hours or more, without heating the temperature after that slowly cooled down to room temperature then allowed to cool for 30 minutes then immersed in running water for 15 minutes. Another polymerization method is at a temperature of 74 °C for 2 hours then increasing the temperature to 100 °C for 1 hour, then slowly cooling it to room temperature then allowed to cool for 30 minutes then immersed in running water for 15 minutes. The boiling point of the monomer is 100.8 ° C, if the temperature of the polymerization process exceeds the boiling point of the monomer, it will cause a lot of porous in acrylic resin, on the other hand, if the temperature of the polymerization process does not reach the boiling point, it causes unreacted monomers. The polymerization method, according to Craig, uses a water bath with a temperature of 74 °C where the monomer boiling point reaches 100.3 °C, if the polymerization process exceeds the monomer boiling point, it causes a lot of porous.

#### 3.2. An Optimally

## An Optimally Solving Dentistry Internal Purity In Heat Polymerized Acrylic Resin With Different Polymerization Methods

The samples of this study were blocks of hot polymerized acrylic resin with a size of 20 mm x 20 mm x 2 mm:



**Fig 2. Sample shape and size**

In this study, the minimum destination sample size was based on Federer's formula:

$$(t - 1)(r - 1) \geq 15$$

definition:

t= Number of treatments

r=Number of repetitions

In this research, 3 treatment groups will be used, namely the polymerization group with different temperatures, namely 25 °C for 0 minutes increased by 74 °C for 90 minutes increased by 100 °C for 60 minutes, 25 °C for 0 minutes increased by 70 °C for 90 minutes increased by 100 °C for 30 minutes, 25 °C for 0 minutes increased by 70 °C for 60 minutes increased by 100 °C for 30 minutes, so that t = 3. Based on the above formula, the number of samples (n) for each group can be determined as follows :

$$(t - 1)(r - 1) \geq 15$$

$$(3 - 1)(r - 1) \geq 15$$

$$2(r - 1) \geq 17$$

$$2r - 2 \geq 17$$

$$r \geq 8.5$$

From the above calculations, the minimum number of samples for each group is 8.5, in this study a sample size of 10 was taken for each treatment group. The total sample in this study was 30 experiments.

### 3.3. Variable Input

#### a) Controlled Variable

Type of hot polymerized acrylic resin, Sample

51

size 20 mm x 20 mm x 2 mm. Heat polymerized acrylic resin ratio (2 g polymer: 1 ml monomer). Cast time setting is 15 minutes. Cast to water ratio according to factory dosage 300 gr: 90 ml. The pressing pressure of the hydraulic cuvette is 1000 psi - 2200 psi. 500 rpm polishing speed. Polishing time 3-5 minutes. Sand paper grid. Opening of the cuvette at 25 °C.

#### b) Uncontrolled Variable

Acrylic resin stirring speed. Cast stirring speed. Stirring time of acrylic until it reaches the dough phase. Time of stirring the cast until it is homogeneous.

### 3.4. Operational definition

Hot polymerized acrylic resin is a denture base material which is formed by mixing a powder containing a polymer and a liquid containing a monomer which polymerizes by heating. Porosity is boasting within the surface at the base of the denture.

## RESULT AND DISCUSSION

In this result obtained were there were differences in the amount of internal porosity with different polymerization methods. The mean and standard deviation of the amount of porosity in sample group A was 31.759 ± 60.317, in sample group B was 7.860 ± 3.141, and in sample group C was 14.150 ± 17.988.

**Table 1. The average number of internal porosities of the hot polymerized acrylic resin with different polymerization methods in sample group A, sample group B and sample group C**

No	Amount porosity		
	experiment A	experiment B	experiment C
1	15,2	5,5	6,4
2	11,1	5,0	5,2
3	7,5	5,6	7,2
4	15,2	8,7	8,1
5	14,7	15,4	64,6
6	16,5	7,3	14,6
7	8,5	7,2	5,0
8	8,0	7,7	11,3
9	10,5	10,5	11,5
10	8,0	5,7	7,6
<b>X ± SD</b>	<b>11,520 ± 3,547</b>	<b>7,860 ± 3,141</b>	<b>14,150 ± 17,988</b>

An Optimally Solving Dentistry Internal Purity In Heat Polymerized Acrylic Resin With Different Polymerization Methods




Figure 3. Result The average number of interporosities of the hot polymerized acrylic resin with different polymerization methods in sample group A, sample group B and sample group C

13

The results of this study also showed that the group in sample C had a higher amount of porosity in the hot polymerized acrylic resin, namely the group in sample C,

namely 14,150. Then after the sample group C, namely group A 11,520. And the last sample group B is 7,860.




Figure 4. The average value of the porosity amount of the hot polymerized acrylic resin

Based on the average graph above, it is known that the highest average number of porosities is in sample group A 31,759, while the lowest number of porosities is in sample group B 7,860. Then there is sample group B, the difference in the amount of porosity in the acrylic resin is much different from the sample group C due to the possibility that it is due to the fast polymerization time in sample group C.8.

different time which revealed that the fast polymerization time the porosity value of the acrylic resin will be more.

To find out whether the data is normally distributed or not, the normality test is performed first. The data normality test used in this study was the Shapiro-Wilk test, then continued by using the Kruskal-Wallis test to see the difference in the amount of porosity of hot polymerized acrylic resin in each group.

Table 2. Normality test using the Shapiro-Wilk test

Classification	Statistics	Df	Sig.
Experiment A	.858	10	.073
Experiment B	.818	10	.024
Experiment C	.520	10	.000



## An Optimally Solving Dentistry Internal Purity In Heat Polymerized Acrylic Resin With Different Polymerization Methods

The results of the Kruskal-Wallis test in Table 3 showed that the value of  $p = 0.205$  ( $p < 0.05$ ), it was concluded that there was no statistically significant difference regarding the amount of internal porosity of hot polymerized acrylic resin with different polymerization methods, namely group A (temperature 25 °C for 0' → 74 °C for 90' → 100 °C for 60'), sample group B (temperature 25 °C for 0' → 70 °C for 90' → 100 °C for 30') and sample group C (temperature 25 °C for 0' → 74 °C for 60' → 100 °C for 30'). This also shows that  $H_0$  (initial hypothesis) is rejected. In this study, the results of the Mann Whitney test in Table 4, the amount of internal porosity of the hot polymerization acrylic resin with different polymerization methods show that there were insignificant / significant differences in sample group A with sample group B, sample group A with sample group C and sample group B with sample group C with a significance value of  $p = < 0.05$ .

### 34 CONCLUSION AND FUTURE WORK

In this study, The results of this study indicated that there was a difference in the amount of internal porosity in the hot polymerized acrylic resin with different methods in sample group A (temperature 25 °C for 0' → 74 °C for 90' → 100 °C for 60'), namely 11,520 in the sample group. B (temperature 25 °C for 0' → 70 °C for 90' → 100 °C for 30') which is 7,860 and the sample group C (temperature 25 °C for 0' → 74 °C for 60' → 100 °C for 30') 14,150. Based on the research of Al-Khafagy et al (2013) who examined conventional polymerization methods with different times, it was said that there was a small amount of porosity at the polymerization time of 74 °C for 2 hours compared to the polymerization time of 100 °C for 30 minutes. The data obtained in this study shows the average and standard deviation of the amount of internal porosity of hot polymerized acrylic resin with different methods, namely sample A group is  $11,520 \pm 3,547$ , sample B group is  $7,860 \pm 3,141$  and sample group C is  $14,150 \pm 17,988$ . In this study, it can be seen that the average porosity value of the hot polymerized acrylic resin by different methods in sample group B (temperature 25 °C for 0' → 70 °C for 90' → 100 °C for 30') has the same porosity. slightly compared to sample A (temperature 25 °C for 0' → 74 °C for 90' → 100 °C for 60') and sample C (temperature 25 °C for 0' → 74 °C for 60' → 100 °C for 30'). This is because if the temperature of the polymerization process does not exceed the boiling point of the monomer, the amount of porosity contained in the acrylic resin will be low, the monomer boiling point is 100.8 °C.

### REFERENCES

1. Kargarzadeh, H., Mariano, M., Huang, J., Lin, N., Ahmad, I., Dufresne, A., & Thomas, S. (2017). Recent developments on nanocellulose reinforced polymer nanocomposites: A review. *Polymer*, 132, 28-393.
2. Sun, J., Forster, A. M., Johnson, P. M., Eidelman, N., Quinn, G., Schumacher, G., ... & Wu, W. L. (2011). Improving performance of dental resins by adding titanium dioxide nanoparticles. *Dental Materials*, 48(10), 972-982.
3. Elshereksi, N. W., Ghazal, M. J., Muchtar, A., & Azhari, C. H. (2014). Perspectives for titanium-derived fillers usage on denture base composite construction: a review article. *Advances in Materials Science and Engineering*, 2014.
4. Lung, C. Y. K., & Matinlinna, J. P. (2012). Aspects of silane coupling agents and surface conditioning in dentistry: an overview. *Dental materials*, 28(5), 467-477.
5. Abood, L. N. (2007). Porosity of different thickness of acrylic polymerized by different methods. *Al-Rafidain Dental Journal*, 7(10), 173-179.
6. Munadzirah, E., & Indrasari, M. (2000). biokompatibilitas bahan basis gigi tiruan resin akrilik. *Journal of Dentistry Indonesia*, 7(1), 116-120.
7. Lima, J. F. M., Maciel, J. G., Hotta, J., Vizoto, A. C. P., Honório, H., Urban, V. M., & Neppelenbroek, K. H. (2016). Porosity of temporary denture soft liners containing antifungal agents. *Journal of Applied Oral Science*, 24(5), 453-461.
8. Aboelsayed, K. M., Mahfouz, O. A., Aboulwafa, O., & Hafez, M. A. (2019). effect of laser and chemical surface treatment of cobalt-chromium alloy on its bond strength with heat cured acrylic resin (comparative laboratory study). *Alexandria Dental Journal*, 44(2), 83-90.
9. Noronha, V. T., Paula, A. J., Duran, G., Galembeck, A., Cogo-Mueller, K., Franz-Montan, M., & Duran, N. (2017). Silver nanoparticles in dentistry. *Dental Materials*, 33(10), 1110-1126.
10. Cao, W., Zhang, Y., Wang, X., Chen, Y., Li, Q., Xing, X., ... & Ye, Z. (2017). Development of a novel resin-based dental material with dual biocidal modes and sustained release of Ag<sup>+</sup> ions based on photocurable core-shell AgBr/cationic polymer nanocomposites. *Journal of Materials Science: Materials in Medicine*, 28(7), 103.
11. Herlina Jusuf, Muhammad Sakti, Ismail Husein, Marischa Elveny, Rahmad Syah, Syahrul Tuba (2020) Modelling Optimally to the Treatment of TB Patients for Increase Medical Knowledge. *SRP*, 11 (4), 742-30. doi:10.31838/srp.2020.4.107.
12. Hubbell, J. A., Pathak, C. P., Sawhney, A., Saini, N., Hossainy, S., & Hill-West, J. L. (2002). U.S. Patent No. 6,465,001. Washington, DC: U.S. Patent and Trademark Office.
13. Pelá, C. A., Rocha, S., De Paula, E., & Baffa, O. (1998). Thermal parameters of dental materials determined by photoacoustic phase lag measurements. *Review of scientific instruments*, 69(9), 3392-3397.
14. Zakir, M., Ashraf, U., Tian, T., Ali, A., Qiao, W., Jin, X., ... & Matinlinna, J. P. (2016). The role of silane coupling agents and universal primers in durable adhesion to dental restorative materials-A review. *Current Oral Health Reports*, 3(3), 244-253.
15. Elveny, M., Syah, R., M.K.M, Nasution. 2020. Taxonomy Business Model Customer Behaviour in E-Metric Ecosystem. *Journal of Advanced Research in Dynamical and Control Systems*. 12(7), pp.99-104. DOI: 10.5373/JARDCS/V12I7/201989.
16. Husein, Ismail H Mawengkang, S Suwilo "Modeling the Transmission of Infectious Disease in a Dynamic Network" *Journal of Physics: Conference Series* 1255 (1), 012052, 2019.
17. Husein, Ismail, Herliana Mawengkang, Saib Suwilo, and Mardiningsih. "Modelling Infectious Disease in Dynamic Networks Considering Vaccine." *Systematic Reviews in Pharmacy* 11.2, pp. 261-266, 2020.
18. Muqdad Irhaem Kadhim, Ismail Husein. "Pharmaceutical and Biological Application of New Synthetic Compounds of Pyranone, Pyridine, Pyrimidine, Pyrazole and Isoxazole Incorporating on 2-Fluoroquinoline Moieties." *Systematic Reviews in Pharmacy* 11 (2020), 679-684. doi:10.5530/srp.2020.2.98.
19. Hamidah Nasution, Herlina Jusuf, Evi Ramadhani, Ismail Husein. "Model of Spread of Infectious

An Optimally Solving Dentistry Internal Purity In Heat Polymerized Acrylic Resin  
With Different Polymerization Methods

- Diseases." *Systematic Reviews in Pharmacy* 11 (2020), 685-689. doi:10.5530/srp.2020.2.99.
20. Husein, Ismail, Dwi Noerjoedianto, Muhammad Sakti, Abeer Hamoodi Jabbar. "Modeling of Epidemic Transmission and Predicting the Spread of Infectious Disease." *Systematic Reviews in Pharmacy* 11.6 (2020), 188-195. Print. doi:10.31838/srp.2020.6.30
  21. Husein, Ismail, YD Prasetyo, S Suwilo "Upper generalized exponents of two-colored primitive extremal minitrans digraphs" AIP Conference Proceedings 1635 (1), 430-439, 2014
  22. S Sitepu, H Mawengkang, I Husein "Optimization model for capacity management and bed scheduling for hospital" IOP Conference Series: Materials Science and Engineering 300 (1), 01,2016.
  23. Herlina Jusuf, Muhammad Sakti, Ismail Husein, Marischa Elveny, Rahmad Syah, Syahrul Tuba. "Modelling Optimally to the Treatment of TB Patients for Increase Medical Knowledge." *Systematic Reviews in Pharmacy* 11 (2020), 742-748. doi:10.31838/srp.2020.4.107
  24. Moosa R, Ghani F. Effect of curing methods and temperature on porosity in acrylic resin denture bases. *J Pak Dent Asso* 11(2); 21 (03): 127-135.
  25. Syah, Rahmad., Nasution, M. K., Elveny, Marischa., & Arbie, Hendra. (2020). Optimization Model for Customer Behavior with MARS and KYC System. *Journal of Theoretical and Applied Information Technology*, 98(13).
  26. Khafagy MT, Al-Musawi RM, Al-Aboudy AT. The effect of using modified flask on the porosity of processed heat-cure acrylic resin. *IJSBAR* 2013; 12(22) 189-196.
  27. Singh S, Palaskar JN, Mittal S. Comparative evaluation of surface porosities in conventional heat polymerized acrylic resin cured by water bath microwavable acrylic resin cured by microwave energy. *Contemp Clin Dent* 2013; 4 (2): 147-151.
  28. Nisar S, Moeen F, Hasan U. Effect of varying curing regimes and powder-liquid ratios on the flexural strength and surface porosities of heat cure acrylic: An in-vitro experiment. *International Journal of Dental Sciences and Research* 2015; 3 (3): 64-71.
  29. R. Syah, M. Elveny and M. K. M. Nasution, "Performance Knowledge Acceleration Optimization with MARS Customer Behavior in Merchant Ecosystem," 2020 3rd International Conference on Mechanical, Electronics, Computer, and Industrial Technology (MECnIT), Medan, Indonesia, 2020, pp. 178-182, doi: 10.1109/MECnIT48290.2020.9166604.
  30. Handajani S, Wulan KA, Fatma D. Pengaruh lama perendaman resin akrilik heat cured dalam larutan cabai rawit terhadap kekuatan impak. *Majalah Kesehatan FK UB* 2013; 44-45.
  31. Istow FPCC, Siagian KV, Pangemanan DHC. Perbedaan kekuatan transversal basis resin akrilik polimerisasi panas pada perendaman minuman beralkohol dan aquades. *Jurnal e-Gigi(eG)* 2015; 3 (3): 398-402.
  32. Agusdarmanto Y, Racmadi P, Arya I W. Perbandingan perubahan warna heat cured acrylic basis gigi tiruan yang direndam dalam klorheksidin dan effervescent (alkaline peroxide). *Dentino* 2014; 2 (2): 205-209.
  33. Hameed KH, Rahn HA. The effect of addition nano particle ZrO2 on some properties of autoclave processed heat cure acrylic denture base material. *J Bagh Collage Dentistry* 2015; 27 (1): 32-39.
  34. Alla RK, Sajjan S, Alluri VR, Ginjupalli K, Upadhya N. Influence of fiber reinforcement on the properties of denture base resins. *JBNB* 2013; 4: 91-97.
  35. R., Nasution, M., Nababan, E. B., Efendi, S. (2020). Knowledge Acceleration Estimator (Kae) Model to Customer Behavior Using Business Metrics. *Journal of Theoretical and Applied Information Technology*, 98(08).
  36. Sitorus Z, Dahar E. Perbaikan sifat fisis dan mekanis resin akrilik polimerisasi panas dengan penambahan serat kaca. *Dentika Dent J* 2012; 17: 24-29.
  37. Ravindranath, Sabarigirinathan C, Vinayagavel K, Rupkumar P, Sriramprabhu G, Choubey A, Elavarasan S, Parimala V, Gandhimathy J. A comparative study to evaluate the mechanical properties of zirconium oxide added polymethyl methacrylate by two different methods at two different concentrations- In vitro study. *Analisis of International medical and dental research*; 1 (3): 161-165.
  38. Unalan F, Dikbas I, Gurbuz O. Transverse strength of polymethylmethacrylate reinforced with different forms and concentrations of e-glass fibres. *OHDMBSC* 2010; 9 (3): 49-7.
  39. Annusavice KJ. *Philips science of dental materials*. 12th Ed., St. Louis Saunders; 2013; 106-110
  40. Ihab NS, Moudhaffar M. Evaluation the effect of modified nano-fillers addition on some properties of heat cured acrylic denture base material. *J Bagh collage dentistry* 2011; 23 (3): 29.
  41. Unalan F, Dikbas I, Gurbuz O. Transverse strength of polymethylmethacrylate reinforced with different forms and concentrations of E-glass fibres. *OHDMBSC* 2010; 9 (3): 144-147.
  42. Rahamneh A, Abdellateef A, Neizel TM. Transverse strength of acrylic resin denture base material after the addition of different fibres. *Pakistan oral & dental journal*. 27 (1): 115-118.
  43. Sitepu, S., Mawengkang, H., & Husein, I. (2018). Optimization Model for Capacity Management and Scheduling for Hospital. *MS&E*, 300(1), 012016.
  44. McCabe JF, Walls AWG. *Applied dental materials*. 9th ed. Oxford: Blackwell, 2008: 110-23.
  45. Karacaer Olat TN, Tezvergil A, Lassila LVJ, Vallittu PK. The effect of length and concentration of glass fibers on the mechanical properties of an injection and a compression- molded denture base polymer. *The journal of prosthetic dentistry* 2003; 90 (4): 385-391.
  46. Husein I., Noerjoedianto, D., Sakti, M., & Jabbar, A. H. (2020). Modeling of Epidemic Transmission and Predicting the Spread of Infectious Disease. *Systematic Reviews in Pharmacy*, 11(6), 188-195.
  47. Powers JM, Sakaguchi RL. *Craig's restorative dental materials*. 12th. Ed. Missouri: Mosby. 2006; 67-70, 88-9, 151, 514-23.
  48. Hatrick CD, Eakle WS, Bird WF. *Dental Material: Clinical Applications for Dental Assistants and Dental hygienists*. 2 th ed. St Louis: Saunders Elsevier, 2011:218-220.
  49. Gladwin M, Bagby M. *Clinical aspect of dental materials theory, practice and cases*. 4th Ed. USA: Philadelphia, 2013: 153-161.
  50. Husein Ismail, R. S. (2020). Model of Increasing Experiences Mathematics Learning with Group Method Project. *International Journal of Advanced Science and Technology*, 1133-1138.
  51. Sadamori S, Ishii T, Hamada T, Razak A. A comparison of three dimensional change in maxillary

*An Optimally Solving Dentistry Internal Purity In Heat Polymerized Acrylic Resin  
With Different Polymerization Methods*

- complete dentures between conventional heat polymerizing and microwave polymerizing techniques. Dent J 2007; 40 (1): 6-10.
52. [32](#)jein, I, Mawengkang, H., & Suwilo, S. (2020). Modelling Infectious Disease in Dynamic Networks Considering Vaccine. Systematic Reviews in Pharmacy, 11(2), 261-266.



# An Optimally Solving Dentistry Internal Purity in Heat Polymerized Acrylic Resin With Different Polymerization Methods

## ORIGINALITY REPORT

20%

SIMILARITY INDEX

13%

INTERNET SOURCES

10%

PUBLICATIONS

8%

STUDENT PAPERS

## PRIMARY SOURCES

- 1 Daniele Silvestri, Stanisław Waclawek, Abhilash Venkateshaiah, Kamil Krawczyk et al. "Synthesis of Ag nanoparticles by a chitosan-poly(3-hydroxybutyrate) polymer conjugate and their superb catalytic activity", Carbohydrate Polymers, 2020  
Publication 1%
- 2 Submitted to Technical University of Cluj-Napoca  
Student Paper 1%
- 3 Submitted to University College London  
Student Paper 1%
- 4 [downloads.hindawi.com](https://downloads.hindawi.com)  
Internet Source 1%
- 5 [www.omicsonline.org](https://www.omicsonline.org)  
Internet Source 1%
- 6 Weiwei Cao, Yu Zhang, Xi Wang, Yinyan Chen, Qiang Li, Xiaodong Xing, Yuhong Xiao, Xuefeng Peng, Zhiwen Ye. "Development of a novel

resin-based dental material with dual biocidal modes and sustained release of Ag<sup>+</sup> ions based on photocurable core-shell AgBr/cationic polymer nanocomposites", Journal of Materials Science: Materials in Medicine, 2017

Publication

- 
- |   |   |    |
|---|---|----|
| 7 | <a href="http://www.doria.fi">www.doria.fi</a><br>Internet Source | 1% |
|---|---|----|
- 
- |   |   |    |
|---|---|----|
| 8 | <a href="http://www.jpda.com.pk">www.jpda.com.pk</a><br>Internet Source | 1% |
|---|---|----|
- 
- |   |   |    |
|---|---|----|
| 9 | <a href="http://s-space.snu.ac.kr">s-space.snu.ac.kr</a><br>Internet Source | 1% |
|---|---|----|
- 
- |    |  |    |
|----|--|----|
| 10 | Bhumika Sharma, Prabal Sharma. "Effect of Incorporation of an Antimicrobial Monomer 2-tert-Butylaminoethyl Methacrylate on the Flexural Strength and Impact Strength of a Heat-polymerized Acrylic Resin: An In Vitro Study", International Journal of Prosthodontics and Restorative Dentistry, 2019<br>Publication | 1% |
|----|--|----|
- 
- |    |   |    |
|----|---|----|
| 11 | Submitted to Wittenborg University<br>Student Paper | 1% |
|----|---|----|
- 
- |    |  |    |
|----|--|----|
| 12 | A. D. Baruwa, Esther T. Akinlabi, O. P. Oladijo, F. M. Mwema. "Chapter 45 Surface Coating Processes: From Conventional to Silane Organic Compound Applications: Recent and | 1% |
|----|--|----|

Prospects", Springer Science and Business  
Media LLC, 2020

Publication

---

13	<a href="http://edoc.pub">edoc.pub</a> Internet Source	1%
14	<a href="http://dfm.ffclrp.usp.br">dfm.ffclrp.usp.br</a> Internet Source	1%
15	T H Nasution, M A Muchtar, S Seniman, I Siregar. "Monitoring temperature and humidity of server room using Lattepanda and ThingSpeak", Journal of Physics: Conference Series, 2019 Publication	<1%
16	"Polishing", Elsevier BV, 2012 Publication	<1%
17	<a href="http://www.id-press.eu">www.id-press.eu</a> Internet Source	<1%
18	Suppachai Howimanporn, Sasithorn Chookaew, Chaiyaporn Silawatchananai. "Comparison between PID and Sliding Mode Controllers for Rotary Inverted Pendulum Using PLC", 2020 4th International Conference on Automation, Control and Robots (ICACR), 2020 Publication	<1%
19	Suryasarathi Bose, P. A. Mahanwar. "Effect of titanate coupling agent on the mechanical,	<1%

---

thermal, dielectric, rheological, and morphological properties of filled nylon 6",  
Journal of Applied Polymer Science, 2006

Publication

20

Suryati Sitepu, Herman Mawengkang, Ismail Husein. "Optimization Model for Capacity Management and Bed Scheduling for Hospital", IOP Conference Series: Materials Science and Engineering, 2018

Publication

<1%

21

[papers.ssrn.com](https://papers.ssrn.com)

Internet Source

<1%

22

[intjdc.org](https://intjdc.org)

Internet Source

<1%

23

[e-journal.unair.ac.id](https://e-journal.unair.ac.id)

Internet Source

<1%

24

Submitted to Universitas Brawijaya

Student Paper

<1%

25

[sintadev.ristekdikti.go.id](https://sintadev.ristekdikti.go.id)

Internet Source

<1%

26

Submitted to Aspen University

Student Paper

<1%

27

[www.juanjunoy.info](http://www.juanjunoy.info)

Internet Source

<1%

28

[repository.maranatha.edu](https://repository.maranatha.edu)

Internet Source

<1%

29

Submitted to Liverpool John Moores University

Student Paper

<1%

30

[www.freepatentsonline.com](http://www.freepatentsonline.com)

Internet Source

<1%

31

[pakmedinet.com](http://pakmedinet.com)

Internet Source

<1%

32

[www.medwelljournals.com](http://www.medwelljournals.com)

Internet Source

<1%

33

Submitted to (school name not available)

Student Paper

<1%

34

Pekka K. Vallittu. "Comparison of the In Vitro Fatigue Resistance of an Acrylic Resin Removable Partial Denture Reinforced With Continuous Glass Fibers or Metal Wires",  
Journal of Prosthodontics, 6/1996

Publication

<1%

35

[gssrr.org](http://gssrr.org)

Internet Source

<1%

36

Submitted to Sunnyslope High School

Student Paper

<1%

37

[www.riejournal.com](http://www.riejournal.com)

Internet Source

<1%



38

H R J Al-abodi, K T M Al-Shaibani, E M Shaker.  
"Molecular investigation of Trichomoniasis in  
women in Al-Muthana province /Iraq", Journal of  
Physics: Conference Series, 2019

Publication

&lt;1%

39

Submitted to University of Liverpool

Student Paper

&lt;1%

40

Christa Hopp, Land. "Considerations for ceramic  
inlays in posterior teeth: a review", Clinical,  
Cosmetic and Investigational Dentistry, 2013

Publication

&lt;1%

41

Submitted to Western Governors University

Student Paper

&lt;1%

42

Submitted to Leeds Trinity and All Saints

Student Paper

&lt;1%

43

[repositorio.unb.br](https://repositorio.unb.br)

Internet Source

&lt;1%

44

Woraporn HOMSIANG, Krid  
KAMONKHANTIKUL, Mansuang  
ARKSORNNUKIT, Hidekazu TAKAHASHI.  
"Effect of zinc oxide nanoparticles incorporated  
into tissue conditioner on antifungal, physical,  
and mechanical properties", Dental Materials  
Journal, 2020

Publication

&lt;1%

45	Submitted to Manipal University Student Paper	<1%
46	"MECnIT 2020 Table of Contents", 2020 3rd International Conference on Mechanical, Electronics, Computer, and Industrial Technology (MECnIT), 2020 Publication	<1%
47	<a href="http://www.ncbi.nlm.nih.gov">www.ncbi.nlm.nih.gov</a> Internet Source	<1%
48	<a href="http://ukm.pure.elsevier.com">ukm.pure.elsevier.com</a> Internet Source	<1%
49	<a href="http://www.ektodermaldisplazi.com">www.ektodermaldisplazi.com</a> Internet Source	<1%
50	<a href="http://www.researchgate.net">www.researchgate.net</a> Internet Source	<1%
51	<a href="http://www.mtixtl.com">www.mtixtl.com</a> Internet Source	<1%
52	<a href="http://yourstrawman.com">yourstrawman.com</a> Internet Source	<1%
53	<a href="http://dergipark.gov.tr">dergipark.gov.tr</a> Internet Source	<1%

Exclude bibliography Off