

# Different Polymerization Methods for Dentistry Amount Internal Porosities: A Systematic Review

*by* Sajaratud Dur Sajaratud Dur

---

**Submission date:** 04-Feb-2021 06:32AM (UTC+0700)

**Submission ID:** 1501054048

**File name:** Different\_polymerization\_methods\_for\_dentistry.pdf (331.59K)

**Word count:** 4575

**Character count:** 23856

# Different Polymerization Methods for Dentistry Amount Internal Porosities: A Systematic Review

Maisyarah Ayu Lubis<sup>1</sup>, Syafiruddin<sup>2</sup>, Ima Frafika Sari<sup>3</sup>,  
M. Daud Batubara<sup>4</sup>, Rahmawaty Samad<sup>5</sup>, \*Marischa Elveny<sup>6</sup>,  
Rahmad Syah<sup>6</sup>, Ismail Husein<sup>7</sup>, Sajaratud Dur<sup>7</sup>, Lely Hilda<sup>8</sup>, Jupriyanto<sup>9</sup>

<sup>1</sup>Faculty of Dentistry, Universitas Sumatera Utara. Medan. Indonesia

<sup>2</sup>Universitas Graha Nusantara

<sup>3</sup>IAIN Ponorogo;

<sup>4</sup>STAIN Mandailing Natal

<sup>5</sup>Universitas Negeri Gorontalo

<sup>6</sup>Faculty of Computer Science and Technology Information, Universitas Sumatera Utara. Medan. Indonesia

<sup>7</sup>Department of Mathematics, Universitas Islam Negeri Sumatera Utara, Medan, Indonesia

<sup>8</sup>IAIN Padangsidimpuan

<sup>9</sup>Universitas Islam Sultan Agung

\*Correspondence email: marischaelveny@usu.ac.id

## ABSTRACT

Data were analysed statistically using the Kruskal-Wallis test to see differences in porosity between 3 different polymerization groups in samples A, B and C. Then continued using the Mann Whitney test to see differences in porosity in each sample A, B and C. heat polymerization acrylic resin with different polymerization methods in sample A (temperature 25 °C for 0' → 74 °C for 90' → 100 °C for 60') compared to sample B (temperature 25 °C for 0' → 70 °C for 90' → 100 °C for 30') and sample C (temperature 25 °C for 0' → 74 °C for 60' → 100 °C for 30'). Sample C (temperature 25 °C for 0' → 74 °C for 60' → 100 °C for 30') had a higher amount of porosity of the hot polymerized acrylic resin with different polymerization methods compared to sample B (temperature 25 °C during 0' → 70 °C for 90' → 100 °C for 30'). There was no significant difference in the amount of internal porosity in the hot polymerized acrylic resin with different polymerization methods in sample A, sample B and sample C.

**Keywords:** Polymerization Methods, Heat Polymerized Acrylic Resins, Measurement Porosity.

## Correspondence:

Nik Syuhailah<sup>22</sup> Nik Hussin

1 Faculty of Entrepreneurship and Business, Universiti Malaysia Kelantan, Locked

Bag 36, Pengkalan Chepa,

16100 Kota Bharu, Kelantan, Malaysia

\*Corresponding author: Nik Syuhailah Nik Hussin email-address:

niksyuhailah@umk.edu.my

## INTRODUCTION

Acrylic resins have been used in dentistry since the mid-1940s for a variety of purposes such as aesthetic coatings, denture crowns and denture elements, orthodontic appliances, repair materials, and removable denture base materials. Acrylic resin has several advantages, namely aesthetics, colour and texture similar to gingiva, low water absorption, easy processing and repair without laboratory experts. Acrylic resin is an ethylene derivative that contains a vinyl group. Generally, there are 7 types of acrylic resin used in dentistry, namely heat cured acrylic resin, self-cured acrylic resin, and light cured acrylic resin. Acrylic resins that are widely used in the manufacture of denture bases are heat cured acrylic resins. Hot polymerized acrylic resin is still widely used in the manufacture of denture bases because of its advantages including satisfactory aesthetic quality, low water absorption, good thermal conductivity, easy processing and repair without the help of laboratory experts as well as being economical, and biocompatible. However, hot polymerized acrylic resin has the disadvantage of having a low impact strength so that it is easy to fracture if it falls on a hard surface. Research conducted by Sahela Nisar et al in 2015 examined the effect of polymerization variations and different powder and liquid ratios on the strength and porosity of acrylic resin, in this study using different specimens, namely 25°C for 0 minutes then increased by 70°C for 90 minutes then raised again. 100°C for 60 minutes, 25°C for 0 minutes then set the temperature to 70°C for 60 minutes, raise the temperature again to 100°C for 30 minutes, 70°C for 0 minutes then raise the temperature again to 100°C for 30 minutes, 100°C for 0 minutes then raise the

temperature again to 100°C for 30 minutes. The results of this study showed a large porosity of the specimens which were directly placed at boiling water temperature of 100°C. This research was conducted to see the amount of internal porosity in hot polymerized acrylic resin when it was carried out using different polymerization methods.

## LITERATURE REVIEW

In this study, this research was conducted with work procedures that can be seen in the chart fig.1.1:

### Manufacture Master Plat

The master plate is made of stainless steel with a size of 20 mm x 20 mm x 2 mm as many as 4 pieces.

### Manufacture Mould

- Make a hard gypsum dough with a ratio of 300 gr: 90 ml of water.
- The dough is stirred with a spatula and made sure that everything is mixed homogeneously.
- The gypsum dough that has been homogeneous is put into the bottom cuvette that has been prepared while vibrating.
- The master plate which has been smeared with Vaseline is placed on the dough in a cuvette until the surface of the master plate and the plaster is even.
- The cast is left to harden for 15-20 minutes until the heat of the cast is gone.
- After the plaster hardens, the upper surface of the plaster and the master plate is smeared with Vaseline. The top cuvette is attached to the bottom cuvette and filled with gypsum dough (ratio of gip to water 300 grams: 90 ml), then the cuvette is

## Different Polymerization Methods for Dentistry Amount Internal Porosities: A Systematic Review

closed and the top and bottom cuvettes are close contact.

- g. After the cast on the upper cuvette hardens, the opened and the master plate is slowly removed mould result is obtained that matches the master.
- h. The mould was smeared with could mould separating medium.

### Hot Polymerized Acrylic Resin Sampling

- a. The polymer and monomer were stirred slowly acrylic pot with a ratio of 23g: 10 ml homogeneous and reached the dough phase. / stage the dough will no longer stick to the touch your hands or a spatula.
- b. After reaching the dough phase, the dough is put mould, then covered with plastic slope and the cuvette is attached and pressed using a manual press.
- c. The cuvette was opened and excess acrylic removed then closed again.
- d. The cuvette was pressed again using a press (upper and lower cuvettes were in close contact press).
- e. The cuvette bolts are fixed and locked to keep the cuvette and the bottom cuvette well adapted.
- f. Polymerization process

### Polymerization (heating)

- a. The polymerization process is carried out inserting the cuvette into a water bath filled with water.
- b. The heating for the sample group A started room temperature 25° C for 0 minutes and increased the temperature to 74° C for 90 minutes then the polymerization process was continued increasing the temperature to 100° C for 30 minutes, after which the water bath was turned off and waited until it reached room temperature so that the cuvette which contains the sample can be removed from the water bath.
- c. The heating for the sample group B started room temperature 25° C for 0 minutes and increased the temperature to 70° C for 90 minutes

then the polymerization process was continued by increasing the temperature to 100° C for 30 minutes, after which the water bath was turned off and waited until it reached room temperature so that the cuvette which contains the sample can be removed from the water bath.

- d. The heating for the sample group C started at room temperature 25° C for 0 minutes and increased the temperature to 70° C for 60 minutes, then the polymerization process was continued by increasing the temperature to 100° C for 30 minutes, after which the water bath was turned off and waited until it reached room temperature for the cuvette which contains the sample can be removed from the water bath.

### Polishing

After the sample came out of the cuvette, the excess acrylic was removed and trimmed using a Fraser bur to remove sharp parts, then with pumice powder using a micromotor, after that it was smoothed using 500, 1000 grid sandpaper and emery paper to smooth the surface of the sample.

### Measurement

To determine the porosity ratio in the sample, the average porosity measurement was carried out for each sample. Using the formula for mean porosity, which is the total number of pores in all viewing areas compared to the number of measurement areas. To see the internal porosity of each sample using a micrograph primo Zeiss star microscope with a magnification of 3000 x, then each sample is divided by 4 viewing areas with a dividing line using a pencil then traced using a microscope, then in each field of view the number of porosity is calculated, after that calculate the average mean porosity that is, the sum of all pores in all viewing areas relative to the total measurement area. Then it will be seen using the percentage in each sample.

## Different Polymerization Methods for Dentistry Amount Internal Porosities: A Systematic Review

### Data Analysis

Data were analysed statistically using the Kruskal-Wallis test to see differences in porosity between 3 different polymerization groups in

samples A, B and C. Then continued using the Mann Whitney test to see differences in porosity in each sample A, B and C.




Fig 1. Research Stages in Measuring Amount Internal Porosity

### MATERIAL

#### Sample Criteria

- A. Inclusion Criteria
  1. Sample in the form of blocks with a size of 20 mm x 20 mm x 2 mm.
  2. The surface of the polished sample is smooth and shiny.
- B. Exclusion Criteria
  1. Sample contaminated with other materials (dirty samples).
  2. Cracked sample.

#### Operational Definition

1. Hot polymerized acrylic resin is a denture base material which is formed by mixing a powder containing polymer and a liquid containing a monomer which polymerizes by heating.
2. Porosity is the bubble in the surface of the denture base. Polymerization is a series of chemical reactions in which macro molecules or polymers are formed from a number of molecules, namely monomers.

Table 1. The average amount of internal porosity of hot polymerized acrylic resin with different polymerization methods in sample group A, sample group B and sample group C.

No	Total porosity		
	specimen A	specimen B	specimen C
1	199,8	5,5	6,4
2	8,8	5,0	5,2
3	4,1	5,6	7,2
4	8,1	8,7	8,1
5	47,3	15,4	64,6
6	13,8	7,3	14,6
7	8,22	7,2	5,0
8	9,25	7,7	11,3
9	10,5	10,5	11,5
10	7,7	5,7	7,6
<b>X ± SD</b>	<b>31,759 ± 60,317</b>	<b>7,860 ± 3,141</b>	<b>14,150 ± 17,988</b>

RESULT AND DISCUSSION

In this result, to find out whether the data is normally distributed or not, the normality test is performed first. The data normality test used in this study was the

Shapiro-Wilk test, then continued by using the Kruskal-Wallis test to see the difference in the amount of porosity of hot polymerized acrylic resin in each group.

Table 2. Normality using the Shapiro-Wilk test

Category	Statistics	Diff	Sig <sup>.</sup>
specimen A	.491	10	.000
specimen B	.818	10	.024
specimen C	.520	10	.000

Based on Table 2, the normality test shows that the amount of porosity in sample A, sample B, and sample C is not normally distributed ( $p > 0.05$ ), so the Kruskal-Wallis

test (nonparametric test) is performed to test whether there is a statistically significant difference.

Table 3. Result Kruskal-Wallis

Methods	Number of Porosity
Chi-Square	3.172
Diff	2
Asymp. Sig <sup>.</sup>	205

Based on table 3 above, it was obtained  $p$  value = 0.205 ( $p < 0.05$ ), it was concluded that there was no statistically significant difference regarding the porosity of hot polymerized acrylic resin with different methods in

sample A, sample B, sample C. that  $H_0$  (initial hypothesis) is rejected. Then the analysis was carried out using the Mann Whitney test to compare between sample groups.

Table 4. Result Mann Whitney

No	Category Specimen	Sig <sup>.</sup>
1.	specimen A with specimen B	.069
	specimen A with specimen C	.0364
2.	specimen B with specimen A	.069
	specimen B with specimen C	.449
3.	specimen C with specimen A	.0364
	specimen C with specimen B	.449

From the results of the Mann Whitney test above, it shows that there is no significant difference with the significance value in the sample group A with the sample group B is  $p = 0.069$  ( $p < 0.05$ ). The comparison between sample group A and sample group C shows the significance value is  $p = 0.0364$  ( $p < 0.05$ ). In the sample group B with sample group A shows a significance value of  $p = 0.069$  ( $p < 0.05$ ) which indicates that there is no meaningful difference between groups. The comparison between sample group B and sample group C shows the significance value is  $p = 0.449$  ( $p < 0.05$ ). In sample group C with sample group A shows a significance value of  $p = 0.364$  ( $p < 0.05$ ) which indicates that there is no significant difference between groups. The comparison between sample group C and sample group B shows the significance value is  $p = 0.449$  ( $p < 0.05$ ).

The results of this study indicate that there is a difference in the amount of internal porosity in hot polymerized acrylic resin with different methods in sample group A (temperature 25 ° C for 0' → 74 ° C for 90' → 100 ° C for 60'), namely 31.759 in the sample group. B (temperature 25 ° C for 0' → 70 ° C for 90' → 100 ° C for 30') is 7,860 and sample group C (temperature 25 ° C for 0' → 74 ° C for 60' → 100 ° C for 30') 14,150. Based on the research of Al-Khafagy et al (2013) who examined conventional polymerization methods with different times, it was said that there was a small amount of porosity at the polymerization time of 74 ° C for 2 hours compared to the polymerization time of 100 ° C for 30 minutes. The data obtained in this study shows the average and standard deviation of the amount of internal porosity of

hot polymerized acrylic resin with different methods, namely sample group A was  $31,759 \pm 60,317$ , sample group B was  $7,860 \pm 3,141$  and sample group C was  $14,150 \pm 17,988$ . In this study, it can be seen that the average porosity value of the hot polymerized acrylic resin by different methods in sample group B (temperature 25 ° C for 0' → 70 ° C for 90' → 100 ° C for 30') has the same porosity, slightly compared to sample A (temperature 25 ° C for 0' → 74 ° C for 90' → 100 ° C for 60') and sample C (temperature 25 ° C for 0' → 74 ° C for 60' → 100 ° C for 30'). This is because if the temperature of the polymerization process does not exceed the boiling point of the monomer, the amount of porosity contained in the acrylic resin will be low, the monomer boiling point is 100.8 ° C.

Then there is sample group B, the difference in the amount of porosity in the acrylic resin is not much different from the sample group C due to the possibility that it is due to the fast polymerization time in sample group C. In accordance with Moosa R's research (2012) on the effect of the polymerization method of acrylic resin on porosity with temperature and different times which reveal that the polymerization time is fast, the porosity value of the acrylic resin will be more.

The results of the Kruskal-Wallis test in Table 3 showed that the value of  $p = 0.205$  ( $p < 0.05$ ), it was concluded that there was no statistically significant difference regarding the amount of internal porosity of hot polymerized acrylic resin with different polymerization methods, namely sample group A (temperature 25 ° C for 0' → 74 ° C for 90' → 100 ° C for 60'), sample group B (temperature 25 ° C for 0' → 70 ° C for 90' → 100 ° C for 30') and sample group C

(temperature 25 °C for 0' → 74 °C for 60' → 100 °C for 30'). This also shows that Ho (initial hypothesis) is rejected. In this study, the results of the Mann Whitney test in Table 4, the amount of internal porosity of the hot polymerized acrylic resin with different polymerization methods show [24](#) at there were insignificant / significant differences in sample group A with sample group B, sample group A with sample group C and sample group B with sample group C with a significance value of p = <0.05.

#### CONCLUSION

- There was a high amount of porosity in the hot polymerized acrylic resin with different polymerization methods in sample A (temperature 25 °C for 0' → 74 °C for 90' → 100 °C for 60') compared to sample B (temperature 25 °C) for 0' → 70 °C for 90' → 100 °C for 30') and sample C (temperature 25 °C for 0' → 74 °C for 60' → 100 °C for 30').
- Sample C (temperature 25 °C for 0' → 74 °C for 60' → 100 °C for 30') had a higher amount of porosity of the hot polymerized acrylic resin by different polymerization methods compared to sample B (temperature 25 °C during 0' → 70 °C for 90' → 100 °C for 30').
- There was no significant difference in the amount of internal porosity in the hot polymerized acrylic resin with different polymerization methods in sample A, sample B and sample C.

#### REFERENCES

- Singh S, Palaskar JN, Mittal S. Comparative evaluation of surface porosities in conventional heat polymerized acrylic resin cured by water bath microwavable acrylic resin cured by microwave energy. *Contemp Clin Dent* 2013; 4 (2): 147-151.
- Putro FPC, Siagian KV, Pangemanan DHC. Perbedaan kekuatan transversal basis resin akrilik polimerisasi panas pada perendaman minuman beralkohol dan aquades. *Jurnal e-Gigi (eG)* 2015; 3 (3): 398-402.
- Munadzirah, E., & Indrasari, M. (2000). biokompatibilitas bahan basis gigi tiruan resin akrilik. *Journal of Dentistry Indonesia*, 7(1), 116-120.
- Kargarzadeh, H., Mariano, M., Huang, J., Lin, N., Ahmad, I., Dufresne, A., & Thomas, S. (2017). Recent developments on nanocellulose reinforced polymer nanocomposites: A review. *Polymer*, 132, 368-393.
- Sun, J., Forster, A. M., Johnson, P. M., Eidelman, N., Mann, G., Schumacher, G., ... & Wu, W. L. (2011). Improving performance of dental resins by adding titanium dioxide nanoparticles. *Dental Materials*, 27(10), 972-982.
- Herlina Jusuf, Muhammad Sakti, Ismail H [34](#), Marischa Elveny, Rahmad Syah, Syahrul Tuba (2020) Modelling Optimally to the Treatment of TB Patients for Increase Medical Knowledge. *SRP*, 11 (4), 742-749. doi:10.31838/srp.2020.4.107.
- Elshereksi, N. W [10](#), Azali, M. J., Muchtar, A., & Azhari, C. H. (2014). Perspectives for titanium-derived fillers usage on denture base composite construction: a review article. *Advances in Materials Science and Engineering*, 2014.
- Nuraini, Diana, Elis Anggeria, Kristina L Silalahi, Ismail Husein, Sajaratud Dur, Sulaiman, Marischa Elveny, Rahmad Syah (2020) Dots Strategic with Extreme Machine Learning Method in The Classification of Disease Transmission in Tb Patients. *Systematic Reviews in Pharmacy*, 11 (3), 5-973. doi:10.31838/srp.2020.3.148
- Lung, C. Y. K., & Matinlinna, J. P. (2012). Aspects of silane coupling agents and surface conditioning in dentistry: an overview. *Dental materials*, 28(5), 467-477.
- Abood, L. N. (2007). Porosity of different thickness of acrylic polymerized by different methods. *Al-Rafidain Dental Journal*, 7(10), 173-179.
- Lima, J. F. M., Maciel, J. G., Hotta, J., Vizoto, A. C. P., Honório [28](#) M., Urban, V. M., & Neppelenbroek, K. H. (2016). Porosity of temporary denture soft liners containing antifungal agents. *Journal of Applied Oral Science*, 24(5), 453-461.
- Fauzi Arif Lubis, Nurlaila, Ismail Husein, Susilawati, Muhammad Lathief Ilhamy Nasution, Marischa Elveny, Afnaria, Nurlama Siregar (2020) Enhancement Model for Hospital Quality Service with Consideration of Integrating Patients Health Insurance to Utilize Fintech. *Systematic Reviews in Pharmacy*, 11 (5), 867-871. doi:10.31838/srp.2020.5.126.
- Aboelsayed, K. M., Mahfouz, O. A., & Hafez, M. A. (2019). effect of laser and chemical surface treatment of cobalt-chromium alloy on its bond strength with heat cured acrylic resin (comparative laboratory study). *Alexandria Dental Journal*, 44(2), 83-90.
- Noronha, V. T., Paula, A. J., Duran, G., Galembeck, A., Cogo-Mueller, K., Franz-Montan, M., & Duran, N. (2017). Silver nanoparticles in dentistry. *Dental Materials*, 33(10), 1110-1126.
- Cao, W., Zhang, Y., Wang, X., Chen, Y., Li, Q., Xing, X., ... & Ye, Z. (2017). Development of a novel resin-based dental material with dual biocidal modes and sustained release of Ag+ ions based on photocurable core-shell AgBr/cationic polymer nanocomposites. *Journal of Materials Science: Materials in Man an edicine*, 28(7), 103.
- Pelá, C. A., Rocha, S., De Paula, E., & Baffa, O. (1998). Thermal parameters of dental materials determined by photoacoustic phase lag measurements. *Review of scientific instruments*, 69(9), 3392-3397.
- Zakir, M., Ashraf, U., Tian [11](#), Han, A., Qiao, W., Jin, X., ... & Matinlinna, J. P. (2016). The role of silane coupling agents and universal primers in durable adhesion to dental restorative materials-A review. *Current Oral Health Reports*, 3(3), 244-253.
- Elveny, M., Syah, R., M.K.M, Nasution. 2020. Taxonomy Business Model [36](#) Customer Behaviour in E-Metric Ecosystem. *Journal of Advanced Research in Dynamical and Control Systems*. 12(7), pp.99-104. DOI: 10.5373/JARDCS/V12I7/20201989.
- Moosa R, Ghani F. Effect of curing methods and temperature on porosity in acrylic resin denture bases. *J Pak Dent Assoc* 2012; 21 (03): 127-135.
- Syah, Rahmad., Nasution, M. K., Elveny, Marischa., & Arbie, Hendra. (2020). Optimization Model for Customer Behavior with MARS and KYC System. *Journal of Theoretical and Applied Information Technology*, 98(13).
- Sajaratud Dur, Ismail Husein, Muqdad Irhaeem Kadhim, Hasan Shamran Mohammed, Marischa Elveny, Rahmad Syah, Lelya Hilda. "An Optimally Solving Dentistry Internal Purity In Heat Polymerized Acrylic Resin With Different Polymerization Methods." *Systematic Reviews in*

- Pharmacy, 11 (2020), 974-980. doi:10.31838/srp.2020.3.149 26
- [22] Al-Khafagy MT, Al-Musawi RM, Al-Aboudy AT. The effect of using modified flask on the porosity of processed heat-cure acrylic resin. *IJSBAR* 2013; 12 (1): 189-196.
- [23] Sugianto, Muslim Marpaung, Siti Munir, Ismail Husein, Purnama Ramadan Silalahi. "The Behavior Of Muslim Investors In Investing In Stocks On The Indonesia Stock Exchange During The Covid-19 Pandemic." *Systematic Reviews in Pharmacy* 11 (2020), 745-752. doi:10.31838/srp.2020.4.109
- [24] Nisar S, Moeen F, Hasan U. Effect of varying curing regimes and powder-liquid ratios on the flexural strength and surface porosities of heat cure acrylic: An in-vitro experiment. *International Journal of Dental Sciences and Research* 2015; 4(16): 64-71.
- [25] Handajani S, Wulan KA, Fatma D. Pengaruh lama perendaman resin akrilik heat cured dalam larutan cabai rawit terhadap kekuatan impak. *Majalah Kesehatan FK UB* 2013; 44-45.
- [26] Agusdarmanto Y, Racmadi P, Arya I W. Perbandingan perubahan warna heat cured acrylic basis gigi tiruan yang direndam dalam klorheksidin dan effervescent (alkaline peroxide). *Dentino* 2014; 2 (2): 205-209.
- [27] Hameed KH, Rahman HA. The effect of addition nano particle ZrO2 on some properties of autoclave processed heat cure acrylic denture base material. *Journal of Collage Dentistry* 2015; 27 (1): 32-39.
- [28] Alla RK, Sajjan S, Alluri VR, Ginpalli K, Upadhy N. Influence of fiber reinforcement on the properties of denture base resins. *JBNB* 2013; 4: 91-97.
- [29] Silitonga R, Nasution M, Nababan E, Efendi S. (2020). Knowledge Acceleration Estimator (Kae) Model to Customer Behavior Using Business Metrics. *Journal of Theoretical and Applied Information Technology*, 98(08).
- [30] Sitorus Z, Dahar E. Perbaikan sifat fisis dan mekanis resin akrilik polimerisasi panas dengan penambahan serat kaca. *Dentika Dent J* 2012; 17: 24-29.
- [31] Unalan F, Dikbas I, Gurbuz O. Transverse strength of polymethylmethacrylate reinforced with different forms and concentrations of e-glass fibres. *OHDMBS* 2010; 9 (3): 144-7.
- [32] Ravindranath, Sabariginathan C, Vinayagavel K, Rupkumar P, Sriramprabhu G, Choubey A, Elavarasan S, Parimala V, Gandhimathy J. A comparative study to evaluate the mechanical properties of zirconium oxide added polymethyl methacrylate by two different methods at two different concentrations- In vitro study. *Analisis of International medical and dental research*; 1 (3): 161-165. 43
- [33] Annusavice KJ. *Philips science of dental materials*. 12th Ed., St. Louis Saunders; 2013; 106-110
- [34] Ihab NS, Moudhaffar M. Evaluation the effect of modified nano-fillers addition on some properties of heat cured acrylic denture base material. *Journal of Collage dentistry* 2011; 23 (3): 23-29.
- [35] Unalan F, Dikbas I, Gurbuz O. Transverse strength of polymethylmethacrylate reinforced with different forms and concentrations of E-glass fibres. *OHDMBS* 2010; 9 (3): 144-147.
- [36] Hamidah Nasution, Herlina Jusuf, Evi Ramadhani, Ismail Husein. "Model of Spread of Infectious Diseases." *Systematic Reviews in Pharmacy* 11 (2020), 685-689. doi:10.5530/srp.2020.2.23 23
- [37] Rahamneh A, Abdelateef A, Neizel TM. Transverse strength of acrylic resin denture base material after the addition of different fibres. *Pakistan oral & dental journal*. 27 (1): 115-118. 19
- [38] Sitepu, S, Mawengkang, H., & Husein, I. (2018). Optimization Model for Capacity Management and Scheduling for Hospital. *MS&E*, 300(1), 012016.
- [39] McCabe JF, Walls AWG. *Applied dental materials*. 9th ed. Oxford: Blackwell, 2008:110-23.
- [40] Karacaer O, Polat TN, Tezvergil A, Lassila LVJ, Vallittu PK. The effect of length and concentration of glass fibers on the mechanical properties of an injection and a compression- molded denture base polymer. *The journal of prosthetic dentistry* 2003; 90 (4): 385-391.
- [41] Husein, I, Noerjoedianto, D., Sakti, M., & Jabbar, A. H. (2020). Modeling of Epidemic Transmission and Predicting the Spread of Infectious Disease. *Systematic Reviews in Pharmacy*, 11(6), 183-195. 32
- [42] Powers JM, Sakaguchi RL. *Craig's restorative dental materials*. 12th. Ed. Missouri: Mosby. 2006; 67-70, 77-8, 88-9, 151, 514-23.
- [43] Muqdad Irhaem Kadhim, Ismail Husein. "Pharmaceutical and Biological Application of New Synthetic Compounds of Pyranone, Pyridine, Pyrimidine, Pyrazole and Isoxazole Incorporating on 2-Flouroquinoline Moieties." *Systematic Reviews in Pharmacy* 11 (2020), 679-684. doi:10.5530/srp.2020.2.98. 8
- [44] Hatrick CD, Eakle WS, Bird WF. *Dental Material: Clinical Applications for Dental Assistants and Dental hygienists*. 2 th ed. St Louis: Saunders Elsevier, 2011:218-220.
- [45] Gladwin M, Bagby M. *Clinical aspect of dental materials theory, practice and cases*. 4th Ed. USA: Philadelphia, 2013: 153-161. 18
- [46] Husein, Ismail H Mawengkang, S Suwilo "Modeling the Transmission of Infectious Disease in a Dynamic Network" *Journal of Physics: Conference Series* 1255 (1), 012052, 2019.
- [47] Husein, Ismail, YD Prasetyo, S Suwilo "Upper generalized exponents of two-colored primitive extremal minstrong digraphs" *AIP Conference Proceedings* 1635 (1), 430-439, 2014
- [48] Husein, Ismail, Dwi Noerjoedianto, Muhammad Sakti, Abeer Hamoodi Jabbar. "Modeling of Epidemic Transmission and Predicting the Spread of Infectious Disease." *Systematic Reviews in Pharmacy* 11.6 (2020), 188-195. Print. doi:10.31838/srp.2020.6.30
- [49] Husein Ismail, R. S. (2020). Model of Increasing Experiences Mathematics Learning with Group Method Project. *International Journal of Advanced Science and Technology*, 1133-1138. 14
- [50] Sadamori S, Ishii T, Hamada T, Razak A. A comparison of three-dimensional change in maxillary complete dentures between conventional heat polymerizing and microwave polymerizing techniques. *Dent J* 2007; 40 (1): 6-10. 17
- [51] Hubbell, J. A., Pathak, C. P., Sawhney, S., Desai, N., Hossainy, S., & Hill-West, J. L. (2002). U.S. Patent No. 6,465,001. Washington, DC: U.S. Patent and Trademark Office. 31
- [52] Husein, I, Mawengkang, H., & Suwilo, S. (2020). Modelling Infectious Disease in Dynamic Networks

*Different Polymerization Methods for Dentistry Amount Internal Porosities: A Systematic Review*

Considertaing **Vaccine**. Systematic Reviews in  
Pharmacy, 11(2), 261-266.



# Different Polymerization Methods for Dentistry Amount Internal Porosities: A Systematic Review

## ORIGINALITY REPORT

17%

SIMILARITY INDEX

12%

INTERNET SOURCES

9%

PUBLICATIONS

7%

STUDENT PAPERS

## PRIMARY SOURCES

1	Submitted to Wittenborg University Student Paper	1%
2	A. D. Baruwa, Esther T. Akinlabi, O. P. Oladijo, F. M. Mwema. "Chapter 45 Surface Coating Processes: From Conventional to Silane Organic Compound Applications: Recent and Prospects", Springer Science and Business Media LLC, 2020 Publication	1%
3	dfm.ffclrp.usp.br Internet Source	1%
4	itechmag.org Internet Source	1%
5	www.fisica.ufc.br Internet Source	1%
6	kclpure.kcl.ac.uk Internet Source	<1%
7	Carmen Beatriz Borges FORTES, Vicente	

Castelo Branco LEITUNE, Fabrício Mezzomo  
COLLARES, Nélio Bairros DORNELLES  
JUNIOR et al. "Acrylic resin disinfection by  
peracetic acid and microwave energy", RGO -  
Revista Gaúcha de Odontologia, 2015

Publication

<1%

8

"Polishing", Elsevier BV, 2012

Publication

<1%

9

[www.id-press.eu](http://www.id-press.eu)

Internet Source

<1%

10

S. Bose, H. Raghu, P. A. Mahanwar. "Mica  
reinforced nylon-6: Effect of coupling agents on  
mechanical, thermal, and dielectric properties",  
Journal of Applied Polymer Science, 2006

Publication

<1%

11

[papers.ssrn.com](http://papers.ssrn.com)

Internet Source

<1%

12

[repository.uinsu.ac.id](http://repository.uinsu.ac.id)

Internet Source

<1%

13

[intjdc.org](http://intjdc.org)

Internet Source

<1%

14

[e-journal.unair.ac.id](http://e-journal.unair.ac.id)

Internet Source

<1%

15

Submitted to Universitas Brawijaya

Student Paper

<1%

16	<a href="http://sintadev.ristekdikti.go.id">sintadev.ristekdikti.go.id</a> Internet Source	<1%
17	<a href="http://www.faqs.org">www.faqs.org</a> Internet Source	<1%
18	Submitted to Liverpool John Moores University Student Paper	<1%
19	Inaki Maulida Hakim, Dea Ananda Nabila. "Optimization Model to Minimize Cost of Inpatient Bed Provision in Public Hospital", Proceedings of the 2019 5th International Conference on Industrial and Business Engineering, 2019 Publication	<1%
20	<a href="http://edoc.pub">edoc.pub</a> Internet Source	<1%
21	<a href="http://repository.maranatha.edu">repository.maranatha.edu</a> Internet Source	<1%
22	<a href="http://www.ijafb.com">www.ijafb.com</a> Internet Source	<1%
23	<a href="http://pakmedinet.com">pakmedinet.com</a> Internet Source	<1%
24	Submitted to (school name not available) Student Paper	<1%
25	Submitted to San Joaquin Valley College Student Paper	<1%

- 
- 26 [www.gssrr.org](http://www.gssrr.org)  
Internet Source <1%
- 
- 27 Xinjian Feng, Jin Zhai, Lei Jiang. "The Fabrication and Switchable Superhydrophobicity of TiO<sub>2</sub> Nanorod Films", *Angewandte Chemie International Edition*, 2005  
Publication <1%
- 
- 28 [bv.fapesp.br](http://bv.fapesp.br)  
Internet Source <1%
- 
- 29 Submitted to Universitas Katolik Indonesia Atma Jaya  
Student Paper <1%
- 
- 30 Nourelhoda M. Mahmoud, Mohamed H. Mahmoud, Salman Alamery, Hassan Fouad. "Structural modeling and phylogenetic analysis for infectious disease transmission pattern based on maximum likelihood tree approach", *Journal of Ambient Intelligence and Humanized Computing*, 2021  
Publication <1%
- 
- 31 [d.lib.msu.edu](http://d.lib.msu.edu)  
Internet Source <1%
- 
- 32 [jurnalpenyakitdalam.ui.ac.id](http://jurnalpenyakitdalam.ui.ac.id)  
Internet Source <1%
- 
- 33 [jurnal.usu.ac.id](http://jurnal.usu.ac.id)

Internet Source

<1%

34

Submitted to Australian Catholic University

Student Paper

<1%

35

Submitted to University of Liverpool

Student Paper

<1%

36

Submitted to Leeds Trinity and All Saints

Student Paper

<1%

37

[repositorio.unb.br](http://repositorio.unb.br)

Internet Source

<1%

38

C Nathan. "Effect of saw dust, rice husk, and groundnut shell on properties of mubi vimtim clay in Adamawa State Nigeria", IOP Conference Series: Materials Science and Engineering, 2020

Publication

<1%

39

[eurekamag.com](http://eurekamag.com)

Internet Source

<1%

40

[www.ncbi.nlm.nih.gov](http://www.ncbi.nlm.nih.gov)

Internet Source

<1%

41

[ir.uitm.edu.my](http://ir.uitm.edu.my)

Internet Source

<1%

42

Rasyid. "The effect of curcumin and placebo on human gall-bladder function: an ultrasound

<1%

study", Alimentary Pharmacology and  
Therapeutics, 2/1999

Publication

---

43 [www.ektodermaldisplazi.com](http://www.ektodermaldisplazi.com) <1 %  
Internet Source

---

44 Submitted to The Robert Gordon University <1 %  
Student Paper

---

45 Fernanda de Carvalho Panzeri Pires-de-Souza, Heitor Panzeri, Marcelo Aparecido Vieira, Lucas da Fonseca Roberti Garcia et al. "Impact and fracture resistance of an experimental acrylic polymer with elastomer in different proportions", Materials Research, 2009 <1 %  
Publication

---

46 [www.podj.com.pk](http://www.podj.com.pk) <1 %  
Internet Source

---

47 [www.journaltoacs.ac.uk](http://www.journaltoacs.ac.uk) <1 %  
Internet Source

---

48 [www.juanjunoy.info](http://www.juanjunoy.info) <1 %  
Internet Source

---

49 [yourstrawman.com](http://yourstrawman.com) <1 %  
Internet Source

---

50 [dergipark.gov.tr](http://dergipark.gov.tr) <1 %  
Internet Source

---

51 [www.karger.com](http://www.karger.com)



Internet Source

<1%

---

Exclude quotes      Off

Exclude matches      Off

Exclude bibliography      Off